



Contribution ID: 103

Type: **Invited talk**

Results from Actual Studies using Pulsed Low Energy Positron Systems

Tuesday 10 December 2019 15:40 (25 minutes)

We are focused on the long term operation of nuclear reactors, which is one of the most discussed challenges in nuclear power engineering. The radiation degradation of nuclear materials limits the operational lifetime of all nuclear installations or at least decreases its safety margin. This paper is focused on experimental simulation and evaluation of materials via hydrogen ion implantation and comparison to our previous results obtained from neutron irradiated samples. The important results were obtained from the near surface studies using Pulsed Low Energy Positron System (PLEPS) in Garching. In our case, German reactor pressure vessel steels, originally from CARINA/CARISMA program, were studied by positron annihilation lifetime spectroscopy and pulsed low energy positron system with the aim to study microstructural changes in RPV steels after high level of irradiation. These results were compared to results from high level of hydrogen nuclei implantation. Defects with the size of about 1-2 vacancies with relatively small contribution (with intensity on the level of 20-40 %) were observed in all "as-received" steels. The increase in the size of the induced defects due to neutron damage was observed in the irradiated specimens resulting in 2-3 vacancies. On the other hand, the size and intensity of defects reached extremely high values due to displacement damage caused due to implantation of hydrogen ions in very narrow damaged region.

Primary authors: Dr PETRISKA, Martin (Slovak University of Technology); Mr SARO, Matus (Slovak University of technology); Dr SOJAK, Stanislav (Slovak University of Technology); Prof. SLUGEN, Vladimir (Slovak University of Technology); Dr EGGGER, Werner (University of Bundeswehr)

Presenter: Prof. SLUGEN, Vladimir (Slovak University of Technology)

Session Classification: Positrons

Track Classification: Positrons