



Contribution ID: 273

Type: Poster

Ordered and disordered variants of the triangular lattice antiferromagnet $\text{Ca}_3\text{NiNb}_2\text{O}_9$

Tuesday 21 March 2023 16:00 (2 hours)

Single crystals of the triangular lattice antiferromagnet (TLAF) $\text{Ca}_3\text{NiNb}_2\text{O}_9$ and its non-magnetic analogue $\text{Ca}_3\text{MgNb}_2\text{O}_9$ are grown using the four-mirror optical float-zone furnace. During the growth of $\text{Ca}_3\text{NiNb}_2\text{O}_9$, the crystal boule tends to develop cracks upon cooling due to a high-temperature structural modification. Thus, depending on the growth conditions, the crystal boules contain varying amounts of high and low-temperature modifications, present in the form of mm-size grains distinguishable on the basis of their appearance: opaque, dark-green (AGO) and translucent, light-green (AGT) for the high and low-temperature modifications, respectively. Furthermore, when the as-grown, AGO specimen is subject to air annealing at 1200°C , its appearance change from opaque to translucent green, without any noticeable change of weight. Low temperature specific heat and low-field magnetization measurements carried out on the AGO and AGT samples revealed contrasting ground state properties. While AGO exhibits a spin-glass-like ground state, the AGT sample exhibit a two-step, long-range antiferromagnetic ordering of the Ni spins with transitions at $T_{\text{N}_1} = 4.6 \text{ K}$ and $T_{\text{N}_2} = 4.2 \text{ K}$. Detailed structural analysis shows that AGO and AGT crystals crystallize in $Pbnm$ (orthorhombic) and $P12_1/c_1$ (monoclinic) space groups, respectively. The high-resolution TEM images confirms the 1:2 ordering of Ni and Nb in the AGT sample. The high-field magnetization up to 50 T in AGT reveals the presence of magnetization plateaus characteristic of TLAFs. The propagation vector in the ordered phase (2 K) is inferred to be $\vec{k} \approx (0, 1/3, 0)$ based on the magnetic neutron scattering.

Authors: Mr OULADDIAF, Bachir (Institut Laue-Langevin); Ms ROUT, Dibyata (Indian Institute of Science Education and Research); SKOULATOS, Markos (TUM); TANG, Ran (Technical University Munich); Mr SINGH, Surjeet (Indian Institute of Science Education and Research)

Co-authors: MIYAKE, Atsushi (The University of Tokyo); TOKUNAGA, Masashi (The University of Tokyo); MAHAPATRA, Sagar (Indian Institute of Science Education and Research); KINOSHITA, Yuto (The University of Tokyo)

Presenter: TANG, Ran (Technical University Munich)

Session Classification: Poster session TUESDAY

Track Classification: Magnetism, Superconductivity, Topological Systems, Magnetic Thin Films and other electronic phenomena