MLZ Conference 2022: Neutrons for Mobility



Contribution ID: 51

Type: Talk

Microstructure and texture evolution for high-temperature α phase in extruded β-containing TiAl alloy

Friday 3 June 2022 09:20 (20 minutes)

Increasing demands on modern turbines require $(\alpha 2+\gamma)$ lamellar-structured TiAl alloys with fine colony size and properly aligned lamellae. As the lamellar structure is formed by the $\alpha \rightarrow \alpha 2 + \gamma$ phase transformation obeying Blackburn OR, the characteristics of lamellar structure depends directly on the high-temperature α phase. Thus, the lamellar structure optimization could be realized by the modification of high-temperature α phase through thermomechanical processing. In this work, the microstructure and texture evolution of hightemperature α phase in TNM alloy during hot extrusion at (α + β) phase field was investigated by high energy X-ray diffraction (HEXRD) and SEM electron back scatter diffraction (SEM-EBSD). Results show that with a small extrusion ratio (E2.25), the microstructure exhibits uniform and equiaxed α grains with a weak (112 -0//ED fiber texture. With the increase of extrusion ratio, the microstructure tends to exhibit bimodal structure (E7.11) consisting of deformed grains, fine primary DRXed grains with $\langle 101^{-}0 \rangle$ //ED, as well as coarse grown grains with $\langle 1120 \rangle$ //ED. The microstructure and texture evolution are resulted from a combination of extrusion parameter and the GB ß phase. The increasing extrusion ratio, on one hand, increases the deformation degree and the extrusion rate, so that the considerable stored energy cannot be released in a short time. On the other hand, the large extrusion ratio elongates the GB β phase leading to more α/β interfaces which served as pining points inhibited the low-angle boundaries to evolve into high-angle boundaries. Both of them keep more deformed α grains orientated with $\langle 10\Gamma 0 \rangle$ //ED retained in the sample with high extrusion ratio. Accordingly, a preferred grain growth happened to the <11-20>-orientated grains due to the high interface energy. Keywords: TiAl alloy, extrusion, texture, high energy X-ray diffraction (HEXRD), SEM-EBSD

Author: Dr ZHANG, Yudong (LEM3 UMR 7239 CNRS, Université de Lorraine)

Co-authors: Dr QIANG, Fengming (University of Lorraine); Prof. KOU, Hongchao (Northwestern Polytechnical University, China); Prof. LI, Jinshan (Northwestern Polytechnical University, China); Prof. BOUZY, Emmanuel (University of Lorraine, France)

Presenter: Dr ZHANG, Yudong (LEM3 UMR 7239 CNRS, Université de Lorraine)

Session Classification: Friday Morning

Track Classification: Main