



Contribution ID: 158

Type: **Talk (20 min + 5 min discussion)**

The half- to full-Heusler transition in $\text{Ni}_{1+x}\text{MnSb}$

Thursday, December 8, 2022 1:40 PM (25 minutes)

Structural voids are a defining feature of the half-Heusler structure. Using temperature-dependent neutron diffraction, the disordering of these vacancies is followed across the $C1_b$ - $L2_1$ transition in samples of $\text{Ni}_{1+x}\text{MnSb}$ for various Ni excesses x , demonstrating the second-order nature of this transition. Structure solution on high-resolution room-temperature neutron diffraction as well as X-ray diffraction data yields a vacancy content in excess of $1 - x$, the concentration of constitutional vacancies in the ideal model of site occupations. This is mirrored by the increased lattice constant during temperature-dependent diffraction on cooling, implying an annihilation of the initial vacancy excess at elevated temperatures. The reason for this very slow time-scale of vacancy concentration equilibration as compared to typical systems will be discussed, and consequences for the materials properties will be pointed out.

P. Neibecker et al., *phys. status solidi B* **259**, 2100174 (2022)

Primary author: LEITNER, Michael

Co-author: NEIBECKER, Pascal

Presenter: LEITNER, Michael

Session Classification: Structure Research

Track Classification: Structure Research